

# SSAB Domex 380LA

## **General Product Description**

SSAB Domex® 380LA is a high-strength low-alloy steel intended for general presswork, bending and forming. SSAB Domex 380LA offers consistent properties that assist modern, rapid production methods.

SSAB Domex 380LA is available in thicknesses of 0.40-3.00 mm and widths up to 1500 mm as coils, slit coils and as cut to length in lengths up to 8.5 meters.

## **Mechanical Properties**

Yield strength R <sub>el</sub>	strength R <sub>el</sub> Tensile strength R <sub>m</sub>		Min Bending Radius 90° Bend 1) 2)	
(MPa)	(MPa)	(min %)	(Ri/t)	
380- 480	440-560	19	0.25xt	

The mechanical properties are valid in the transverse direction of rolling

## Chemical Composition (Ladle analysis)

С	Si	Mn	Р	S	Al	Nb + Ti
(max %)	(min %)	(max %)				
0.10	0.50	1.20	0.030	0.025	0.015	0.10

#### **Tolerances**

#### Thickness and width

SSAB Domex 380LA is supplied with thickness and width tolerances in accordance with EN 10131. More narrow thickness tolerances according to the SSAB standard are available on request.

#### Length

Cut to length material is supplied to length tolerances in accordance with EN 10131.

## **Delivery Conditions**

Cold rolled.

### **Fabrication and Other Recommendations**

For information concerning welding and fabrication, see SSAB's brochures on www.ssab.com or consult Tech Support, techsupport@ssab.com. Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on the product.

#### **Contact Information**

www.ssab.com/contact



<sup>\*)</sup> When the thickness is less than or equal to 0.7 mm, the minimum value for elongation is reduced by 2 units.

<sup>1)</sup> t = Sheet thickness

<sup>&</sup>lt;sup>2)</sup> For rolling direction and transverse direction