

## SSAB Domex 460LA

### General Product Description

SSAB Domex® 460LA is a high-strength, low-alloy steel for operations that require higher strength. It offers consistent properties for modern, rapid production methods.

SSAB Domex 460LA is available in thicknesses of 0.50-3.00 mm and widths up to 1500 mm as coils, slit coils and as cut to length in lengths up to 8.5 meters.

### Mechanical Properties

Yield strength $R_{el}$ (MPa)	Tensile strength $R_m$ (MPa)	Elongation $A_{80}$ <sup>1)</sup> (min %)	Min Bending Radius 90° Bend <sup>1) 2)</sup> (Ri/t)
460- 580	510- 660	13	0.5xt

The mechanical properties are valid in the transverse direction of rolling.

<sup>1)</sup> When the thickness is less than or equal to 0,7 mm and greater than 0,5 mm, the minimum value for elongation is reduced by 2 units. For a thickness less than or equal to 0,5 mm, the minimum value is reduced by 4 units.

<sup>1)</sup> t = Sheet thickness.

<sup>2)</sup> For rolling direction and transverse direction.

### Chemical Composition (Ladle analysis)

C (max %)	Si (max %)	Mn (max %)	P (max %)	S (max %)	Al (min %)	Nb + Ti (max %)
0.10	0.60	1.50	0.030	0.025	0.015	0.10

### Tolerances

#### Thickness and width

SSAB Domex 460LA is supplied with thickness and width tolerances in accordance to EN 10131. More narrow thickness tolerances according to the SSAB standard are available on request.

#### Length

Cut to length material is supplied with length tolerances in accordance to EN 10131.

### Delivery Conditions

Cold rolled.

### Fabrication and Other Recommendations

For information concerning welding and fabrication, see SSAB's brochures on [www.ssab.com](http://www.ssab.com) or consult Tech Support, [techsupport@ssab.com](mailto:techsupport@ssab.com).

Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on the product.

### Contact Information

[www.ssab.com/contact](http://www.ssab.com/contact)